

MonarVap® SD2 RE


Application:

The Monarvap SD2 RE is a conventional vapour check for use in roofs and walls. In addition the membrane is ideal for use as a refurbishment membrane where the membrane is applied between the rafter battens from the outside.

The sand coloured side facing towards the warm side.

Properties:

The MonarVap SD2 RE has very high nail and tensile strength due to its reinforcement grid. In addition the product is approved as a Halogen Free Flame Retardant Class E membrane.

Product data				
Built-up Top side	Ethylene based copolymer (sand colour)			
Reinforcing	Leno weave grid 8x8 mm			
Bottom side	Nonwoven PP spunbond (white colour)			
Colour	Sand/white			
Weight	135 g/m ² +10% / - 5%		EN 1849-2	
Application	As conventional vapour check for use on the warm side or as refurbishment membrane applied in cold roof applications. Ensure a minimum of 100 mm overlap and ensure that all penetrations/joints must be sealed with suitable tape or Icopal Butyl sealer.			
Technical data	Unit	Value	Tolerance	Test method
Length	m	50		EN 1848-2
Width	m	1,50	+1,5% -½%	EN 1848-2
Straightness		Pass		EN 1848-2
Product Thickness	mm	0,540	±10%	EN 1849-2
Layer Thickness	mm	0,240	±10%	MFX internal test method 20
Visible defects		Pass		EN 1850-2
Tensile strength	N/50 mm	MD >400		EN 12311-2
		TD >400		EN 12311-2
Elongation	%	MD >16		EN 12311-2
		TD >14		EN 12311-2
Nail tear resistance	N	MD >250		EN 12310-1
		TD >250		EN 12310-1
Cold flexibility	°C	- 20°C		EN 1109
Impact resistance	mm	<200 (rigid support)		EN 12691, Method A
Sd value	m	2	+3 / -0	EN 1931
Water vapour transm.	kg/m ² s	2,0 * 10 ⁻⁷	± 0,5 * 10 ⁻⁷	EN 1931
Water tightness	2 kPa	Pass		EN 1928, Method A
Fire classification	Class	E		EN 13501-1
Ageing after EN 1296				
Water vapour transm.	Pass/Fail	Pass		EN 1931
Classification	Vapour Barrier Type A – EN 13984			
				Monarflex s.r.o. Továrenská 1 SK-94303 Stúrovo Slovakia
				10